

Product Information



METCON MCC - 2301 QUICKSET FAST DRYING FINISH PAINT

➤ **PRODUCT DESCRIPTION**

Metcon MCC - 2301 fast Drying finish paint has been widely used in the vehicle refinishing field as it has very fast drying properties and it exhibits very good colour & gloss retention properties. It shows longlasting adhesion on the treated M.S. Substrate with outstanding corrosion resistance properties when applied over Epoxy Zinc Phosphate Primer.

➤ **RECOMMENDED USAGE**

MCC – 2301 is used as a quick drying finish coat for tippers, trailers commercial vehicle, new equipments finishes, industrial finishes, construction steelworks also. It can be top coated over fast drying primer or Epoxy Primer.

➤ **DIRECTIONS FOR USE**

Ensure that the surface is oil and grease free clean and dry. Loose is to be removed or Rust Converter may be applied as a protective measure. Add recommended thinner to adjust application viscosity and apply with brush or spray.

➤ **TECHNICAL SPECIFICATION**

1. TYPE	Fast drying
2. SHADE	Any Standard shade
3. FINISH	Glossy, Semiglossy, Egg shell and Matt.
4. VOLUME SOLIDS	40 + 2%
5. THEROTICAL COVERAGE	10 m ² per ltr at 40 microns DFT
6. DRYING TIME	Surface dry : 15 - 20 mins Tack free dry : 2 - 3 hrs Hard dry : Over night
7. APPLICATION VISCOSITY	25 - 28 secs at 30°C by ford cup B4
8. THINNER	Special Thinner
9. APPLICATION METHOD	Air less or air assisted spray
10. FLASH POINT	>35°C
11. SURFACE PREPARATION	Proper cleaning of the metal surface will enhance the life of the coating. Clean and wipe the surface to get free from dust, rust scale, loose particles and grease.
12. RECOMMENDED DFT	40 - 45 Microns
13. PACKING	20 litres single pack
14. SHELF LIFE	One year in sealed drums
15. CLEAN UP	It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.
16. SAFETY PRECAUTIONS	Both polymer and thinner are rapid drying type. Always paint with small quantity and replace lid after use. Use safety precautions regarding Flammability of Solvents and paints.

The information contained above is given in good faith but without warranty as the method and conditions of use of our products are beyond our control. For further details on application and precautions please contact:

METCON COATINGS & CHEMICALS (INDIA) PVT. LTD.

ISO 9001 : 2008 Certified

Works & Admn. Office : Plot No. C-310, Pawne Village, TTC MIDC Area,
Pawne, Navi Mumbai-400 705. Maharashtra (India)
Tel.: 91 (22) 41412424 (100 lines)
E-mail: info@metconcoatings.com Website: www.metconcoatings.com