



Product Information



METCON MCC – 2501 VINAC COPOLYMER PAINT

➤ **PRODUCT DESCRIPTION**

MCC – 2501 Vinac Copolymer Paint is a fast drying coating exhibiting an excellent Colour /gloss retention, elasticity, scratch hardness, weathering and resistance to mild acids and alkalis and salt water. It gives excellent adhesion to various substrates like mild steel, copper, brass, treated aluminum, concrete without pre-treatment.

➤ **RECOMMENDED USAGE**

MCC – 2501 is used as a self priming primer cum finish coat for exterior steelwork in mild to moderate corrosive atmosphere. It is used in Paper Industries, Pharmaceutical companies, Construction Formworks and inside Tipper bodies & Trailers.

➤ **DIRECTIONS FOR USE**

Ensure that the surface is oil and grease free clean and dry. Loose rust is to be removed or Rust convertor may be applied as a protective measure. Add recommended thinner to adjust application viscosity and apply with brush or spray.

➤ **TECHNICAL SPECIFICATION**

1. TYPE	Acrylic resin based
2. SHADE	Any Standard Shade
3. FINISH	Semiglossy / Eggshell
4. RECOMMENDED THINNER	Vinac Thinner
5. SOLID CONTENTS BY WT	40%
6. DRYING PROPERTIES	Surface Dry: 10 – 15 mins Tack Free: 30 – 40 mins Hard Dry : Overnight
7. THEORETICAL COVERAGE	12 sq mtr/litre @ 35 microns dft
8. APPLICATION VISCOSITY (30°C)	20 – 25 seconds
9. FLASH POINT	> 35°C
10. SURFACE PREPARATION	Proper cleaning of the metal surface will enhance the life of the coating. Clean & wipe the surface to get free from dust, rust scale, loose particles and grease.
11. APPLICATION METHOD	Brush or spray or dipping.
12. RECOMMENDED DFT	30 - 40 microns
13. SHELF LIFE	One year in sealed drums
14. PACKING	20 Litres single pack
15. CLEAN UP	It is good working practice to periodically flush out spray equipment during the course of the working day.
16. SAFETY PRECAUTIONS	Both polymer and thinner are rapid drying type. Always paint with small qty and replace lid after use. Use safety precautions regarding Flammability of Solvents & Paints.

The information contained above is given in good faith but without warranty as the method and conditions of use of our products are beyond our control. For further details on application and precautions please contact:

METCON COATINGS & CHEMICALS (INDIA) PVT. LTD.

ISO 9001 : 2008 Certified

Works & Admn. Office : Plot No. C-310, Pawne Village, TTC MIDC Area,
Pawne, Navi Mumbai-400 705. Maharashtra (India)
Tel.: 91 (22) 41412424 (100 lines)
E-mail: info@metconcoatings.com Website: www.metconcoatings.com